



Manufacturers and distributors of sealing and
jointing materials.

DATA / SPECIFICATION SHEET

ASME m and y Values. Sheet Materials

MATERIAL	THICKNESS (mm)	m FACTOR	y lbf/in ²	y MPa
NOVUS 10	0.75	2.00	2175	15.0
	1.5	2.75	3625	25.0
	3	3.50	4350	30.0
NOVUS 20	0.75	2.00	2175	15.0
	1.5	2.75	3625	25.0
	3	3.50	4350	30.0
NOVUS 21	0.75	2.00	2175	15.0
	1.5	2.75	3625	25.0
	3	3.50	4350	30.0
NOVUS 30	0.75	2.00	2175	15.0
	1.5	2.75	3625	25.0
	3	3.50	4350	30.0
NOVUS 34	0.75	2.00	2175	15.0
	1.5	2.75	3625	25.0
	3	3.50	4350	30.0
NOVUS 45 ACID	0.75	2.00	2000	13.8
	1.5	2.50	3500	24.1
	3	3.00	4100	28.3
NOVUS GRAFTEC	0.75	2.00	2000	13.8
	1.5	2.50	3500	24.1
	3	3.00	4100	28.3
NOVUS UNIFLON 50	1	2.80	1500	10.3
	1.5	3.00	1600	11.0
	3	3.80	2500	17.2
NOVUS UNIFLON 51	1	3.00	2150	14.8
	1.5	3.50	2450	16.9
	3	4.00	2750	19.0
NOVUS UNIFLON 53	1	3.00	2100	14.5
	1.5	3.50	2450	16.9
	3	4.00	2850	19.7
NOVUS TI		2.50	4000	27.6
NOVUS FI		2.00	900	6.2
Sigraflex Hochdruck		2.50	4000	27.6
ElastaGraph		1.50	800	5.5

As the company's products are used for a multiplicity of purposes and as the company has no control over the method of their applications or use, the company excludes all conditions or warranties, expressed or implied by statute or otherwise, as to their products and/or their fitness for any particular purpose. Any technical co-operation between the company and the customer is given for customers assistance only and without liability on the part of the company.