



Novus Sealing Pty Ltd

15 Vinnicombe Drive,
Canning Vale WA 6155

Tel (08) 9455 2155

Fax (08) 9455 2165

ACN 057 426 909

ABN 28 057 426 909

Neoprene Sponge

Base Polymer:	Polychloroprene
Specific Gravity:	160kg/m ³ +/-30kg/m ³
Tensile Strength:	4.0kg/cm ² min.
Operating Temperature: (indirect heat)	-30°C to +100°C
Hardness:	HS (c- type) 25 +5
Elongation:	150% min.
Compression Strength:	(25%) 30kg/100cm ² +/-10
Water Absorption:	0.005g/cm ² max
Compression Set:	(50%, 20°C x 22hrs) 25% max
Heat Shrinkage:	(70°C x 4hrs) 4% max
Fire Retardent:	UL 94HF 1
Test Method:	M 3014 & M 6550